

Abstract:

-21-

A multilayer composite which comprises the following layers:

5

I. an interior layer I selected from among a fluoropolymer molding composition and a polyolefin molding composition;

10

II. a bonding agent layer II which has the following composition:

a) from 0 to 80 parts by weight of a polyamine-polyamide graft copolymer ,

b) from 0 to 85 parts by weight of polyamide,

15

c) from 0 to 85 parts by weight of a polymer selected from among fluoropolymers and polyolefins,

with the sum of the parts by weight of a), b) and c) being 100,

and, in addition,

20

- the sum of the components a) and b) comprising at least 20 parts by weight of monomer units derived from caprolactam and/or the combination hexamethylenediamine/adipic acid,

25

hexamethylenediamine/suberic acid, hexamethylenediamine/sebacic acid, hexamethylenediamine/dodecanedioic acid, hexamethylenediamine/isophthalic acid or hexamethylenediamine/terephthalic acid and

30

d) not more than 50 parts by weight of additives selected from among impact-modifying rubber and customary auxiliaries and additives;

III. a layer III comprising an EVOH molding composition,

35 has improved adhesion of the layers.